

Filter Media Specifications

Standard Media

5 µm Polyester

- 5 Micron, 99+% efficiency
- ID: "odd nbr.": i.e. **19**, **235P**
- Media classification: F8
- Pleated industrial needle felt polyester media
- Plastisol potting
- Temperature min: -26°C (-15°F), max: 104°C (220°F)
- Reinforced epoxy coated steel wire on ID and OD

2 µm Paper

- 2 Micron, 99+% efficiency
- ID: "even nbr.": i.e. **18**, **234P**
- Media classification: F9
- Heavy duty industrial strength paper
- Plastisol potting
- Heavy gauge galvanized expanded metal
- Temperature min: -26°C (-15°F), max: 104°C (220°F)

High Efficiency

1 µm Polyester - Z Media

- 1 Micron, 99+% efficiency
- ID: "odd nbr." & "Z" suffix: i.e. **19Z**, **235ZP**
- Media classification: F9
- Epoxy coated steel wire on both sides of media
- Temp min: -26°C (-15°F), max: 104°C (220°F)
- Washable - lukewarm water & mild detergent

4 µm Polyester - N Media

- 4 Micron, 99+% efficiency
- ID: "odd nbr." & "N" suffix: i.e. **15N**, **377NP**
- Media classification: F9
- Temp min: -26°C (-15°F), max: 104°C (220°F)

H13 - HE Media

- 0.3 Micron, 99,97% efficiency
- ID: "HE" prefix & "even nbr.": i.e. **HE230**, **HE334P**
- Heavy duty industrial strength glass surrounded by heavy gauge galvanized expanded metal
- Maximum oversizing required to minimize pressure drop
- Plastisol potting standard
- Temp min: -26°C (-15°F), max: 104°C (220°F)
- Options: silicone potting, Viton gaskets
- Temp max: 190°C (375°F)

H14 - UL Media

- 0.1 Micron, 99,995% efficiency
- ID: "UL" prefix & "even nbr.": i.e. **UL234**
- Plastisol potting
- Temp min: -26°C (-15°F), max: 104°C (220°F)
- Options: silicone potting, Viton gaskets
- Temp max: 190°C (375°F)

Dutch Twill Weave - DT Media

- ID: "DT" prefix & "odd nbr.": i.e. **DT245**
- Media classification: F9
- Stainless steel woven wire cloth
- Viton gaskets & epoxy potting
- Temp min: -26°C (-15°F), max: 190°C (375°F)



Chemical/Food/Pharmaceutical

Stainless Steel Wire Mesh- S2Media

- Stainless steel pleated wire mesh
- ID: "even nbr." & "S2" suffix: i.e. **14S2**
- Stainless steel expanded metal
- Chemical resistant and high temperature resistant
- Available with silicone endcaps

Polypropylene (PP) - Y Media

- 5 Micron, 99+% efficiency
- ID: "odd nbr." & "Y" suffix: i.e. **31N**, **345YP**
- Media classification: F8
- Epoxy coated steel wire on ID and OD

PTFE - TG Media, 0.3 micron, 99,5% efficiency

- ID: "TG" prefix & "odd nbr.": i.e. **TG375**
- Media classification: E12
- High temperature, chemical, & moisture resistant
- Options: Viton gaskets, epoxy potting
- Temp (intermittent): Up to 250°C (482°F)

PTFE - TF Media, 0.3 micron, 99,5% efficiency

- ID: "TF" prefix & "odd nbr.": i.e. **TF275**
- Media classification: E12
- Chemical & moisture resistant
- Minimal pressure drop
- Temp (intermittent): 104°C (220°F)
- Options: Viton gaskets, epoxy potting

PPS - RY Media

- Broad chemical resistant media, high temp
- ID: "RY" prefix & "odd nbr.": i.e. **RY485**
- Media classification: F8
- Temp min: -26°C (-15°F), max: 104°C (220°F)
- Options: Viton gaskets, epoxy potting

Filter Media Specifications



High Temperature

Nomex - MX Media

- 5 Micron, 99+% efficiency
 - ID: "odd nbr." & "MX" suffix: i.e. 377MX
 - Media classification: F8
- Silicone potting
- Temperature min: -26°C (-15°F), max: 196°C (385°F)
- Reinforced epoxy coated steel wire on ID and OD

Nomex with Stainless Steel Support- MXD Media

- 5 Micron, 99+% efficiency
 - ID: "odd nbr." & "MX" suffix: i.e. 377MXD
 - Media classification: F8
- Silicone potting
- Reinforced stainless steel wire mesh on ID and OD
- Temperature min: -26°C (-15°F), max: 196°C (385°F)

Chemical Adsorption

Activated Carbon - AC Media

- 10 Micron, 99+% efficiency
- ID: "AC" prefix & "even nbr.": i.e. AC18
- Removes gas or vapor odors, contaminants, & particulate
- Pleated media
- Reinforced with epoxy coated steel wire on both sides of cloth

Activated Carbon Granulate- ACG Media

- ID: "ACG" prefix & "even nbr.": i.e. ACG230
- Removes gaseous or vapor odors
- Granulates are enclosed within a polyester wrap and expanded metal on the I.D. and O.D.

Activated Alumina- AA Media

- ID: "AA" prefix & "even nbr.": i.e. AA850
- Desiccant used in the adsorption of water & oil vapour & the prevention of backstreaming in pumps
- Adsorbs up to 40% of media's weight

Electrostatic Activated Carbon- GM Media

- 3 Micron, 70% efficiency
- ID: "GM" prefix & "odd nbr.": i.e. GM35
- Superior odor removal
- Chemically inert
- Electrostatic fibers attract & hold particles

Coalescing Media

PSG Media, FG Media, GL Media

- 0.3 Micron, 99,97% efficiency
- ID: "PSG" prefix & "even nbr.": i.e. PSG344
- ID: "FG" prefix: i.e. FG9
- ID: "GL" prefix: i.e. GL915
- Heavy duty industrial glass media, reinforced with epoxy coated steel wire & expanded metal
- Continuous operating temp: 20°C (68°F) to 80°C (180°F)
- Environmentally friendly sealing material
- High D.O.P. efficiency - low oil carryover
- Multiple media configurations, contact factory

Coarse Efficiency

25 µm Polyester - U Media

- 25 Micron, 99+% efficiency
- ID: "odd nbr." & "U" suffix: i.e. 19U, 685UP
- Media classification: F7
- Temp min: -26°C (-15°F), max: 104°C (220°F)

100 µm Polyester - W Media

- 100 Micron, 99+% efficiency
- ID: "odd nbr." & "W" suffix: i.e. 15W, 385WP
- Media classification: M6
- Temp min: -26°C (-15°F), max: 104°C (220°F)

Wire Mesh - S Media

- Epoxy coated pleated wire mesh
- ID: "even nbr." & "S" suffix: i.e. 274S, 344SP
- Expanded metal
- Temp min: -26°C (-15°F), max: 104°C (220°F)

Stainless Steel - S2Media

- Stainless steel pleated wire mesh
- ID: "even nbr." & "S" suffix: i.e. 234S2
- Chemical resistant and high temperature resistant
- Stainless steel expanded metal
- Temp min: -26°C (-15°F), max: 104°C (220°F)
- Options: silicone or epoxy potting, Viton gaskets

Note 1: Elements rated for higher temperatures can be achieved with optional gasket material and potting compounds.

Note 2: Media classifications are best estimates based on EN 779:2012.

Contact Factory for Alternate Media