

Technical Data sheet: FP2 Filter Paper - AIR



Parameter	Value	Dimension	Test Instruction No.
Grammage - impr., air-dry	130 ± 10	g/m ²	3 (ISO 536)
Thickness plain Load 10N/cm ²	0.46 ± 0.10	mm	4 (ISO 534)
Resin Content	19 ± 4	%	20
Air Permeability	930 ± 100	l/m ² s	1 (EN/ISO 9237) @2mbar / A=20cm ²
Burst Strength - Uncured - Cured	≥ 130 ≥ 200	kPa kPa	(EN/ISO 2758) 6 6
Pore Size - max. - many	89 ± 8 78 ± 6	µm µm	5 5

